

DeWitt Company, Inc.
Truck Tarps Specifications

<u>Property</u>	<u>Test Method</u>	<u>Units</u>	<u>Value</u>
<u>Poly Truck Tarp</u>			
Weight	ASTM D-3776	OZ/SQYD	4.30-4.40
Tensile – Warp	ASTM D-5034	LB	84.0
Tensile – Fill	ASTM D-5034	LB	118.0
Elongation – Warp	ASTM D-5034	%	32
Elongation – Fill	ASTM D-5034	%	45
Material			Polypropylene
<u>Knitted Truck Tarp</u>			
Weight	ASTM D-3776	OZ/SQYD	3.48
Breaking Strength (Grab Method)	ASTM D-5034	lbs	Warp – 75 Fill – 65
Breaking Elongation (Grab Method)	ASTM D-5034	%	Warp – 38 Fill – 115
Trapezoid Tear Strength	ASTM D-5587 (Opt. #1)	lbs	Warp – 38 Fill – 116
Burst Strength	ASTM D-3786	PSI	127
<u>Woven Truck Tarp</u>			
Weight	ASTM D-3776	OZ/SQYD	4.3
Construction			20 X 17
Air Porosity	ASTM D-737		450+cfm
Yarn			Warp – Oval Fill – Oval
Tensile Strength	ASTM D-1682	lbs	Warp - 230 Fill – 165
Elongation	ASTM D-1682	%	Warp – 15 Fill – 12
Tear Strength	ASTM D-2261	lbs	Warp – 90 Fill – 70
Puncture Strength	ASTM D-3787	lbs	100
Burst Strength	ASTM D-3786	lbs/in ²	435

Date: 04-28-03. This data sheet supersedes all previously issued data.
The above properties are typical averages.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS, SUCH INFORMATION IS TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE AND RELIABLE AS THE DATE COMPLIED. HOWEVER NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. WE DO NOT ACCEPT LIABILITY FOR ANY LOSS OR DAMAGE THAT MAY OCCUR FROM THE USE OF THIS INFORMATION NOR DO WE OFFER ANY WARRANTY AGAINST PATENT INFRINGEMENT.