

DeWitt Company, Inc. Sunbelt Specifications

<u>Typical Properties</u>	<u>Test Method</u>	
• Material		Polypropylene
• Color		Black with gold stripe every 12"
• Construction		22 x 11
• Weight (oz/SY)	ASTM D-3776	3.2
• Tensile Strength (lbs)	ASTM D-4632	175 x 110
• Burst (psi)	ASTM D-3786	310
• Trapezoid Tear (lbs)	ASTM D-4533	80 x 60
• Puncture (lbs)	ASTM D-4833	50
• Water Permeability (gal/min/SF)	ASTM D-4491	15
• Ultraviolet Exposure (% Strength Retained)	ASTM D-4355	>70% after 2500 Hrs. Xenon Arc Exposure
• Thickness (mils)	ASTM D-1777	17
• Elongation (%)	ASTM D-4632	Warp 15% Weft 18%

Date: 10/1/2000. This data sheet supersedes all previously issued data.
The above properties are typical averages.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS, SUCH INFORMATION IS TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE AND RELIABLE AS THE DATE COMPLIED. HOWEVER NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. WE DO NOT ACCEPT LIABILITY FOR ANY LOSS OR DAMAGE THAT MAY OCCUR FROM THE USE OF THIS INFORMATION NOR DO WE OFFER ANY WARRANTY AGAINST PATENT INFRINGEMENT.

DeWitt Company, Inc.
Ultra Web 3000 Specifications

<u>Typical Properties</u>	<u>Test Method</u>	
• Material		Polypropylene Circular
• Color		Black with orange stripe
• Construction		10 x 10 Ultrasonic
• Weight (oz/SY)	ASTM D-3776	2
• Tensile Strength (lbs)	ASTM D-4632	80 x 80
• Burst (psi)	ASTM D-3786	260
• Trapezoid Tear (lbs)	ASTM D-4533	65
• Puncture (lbs)	ASTM D-4833	55
• Water Permeability (Gal/min/SF)	ASTM D-4491	9
• Ultraviolet Exposure (% Retention in strength)	ASTM D-4355	>50% after 3000 Hrs.
• Thickness (mils)		0

Average deviation shall be +/- 10% of the above value.

Date: 12/09/2005. This data sheet supersedes all previously issued data.

The above properties are typical averages.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS. SUCH INFORMATION IS TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE AND RELIABLE AS THE DATE COMPLIED. HOWEVER NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. WE DO NOT ACCEPT LIABILITY FOR ANY LOSS OR DAMAGE THAT MAY OCCUR FROM THE USE OF THIS INFORMATION NOR DO WE OFFER ANY WARRANTY AGAINST PATENT INFRINGEMENT.

DeWitt Company, Inc.
White Ground Cover Specifications

<u>Physical Property</u>	<u>Test Method</u>	<u>Typical Value</u>	<u>English Units</u>
Composition			Polypropylene
Construction (per inch)			16 Warp 12 Fill
Weight	ASTM D-3776	3.2	OZ/YD2
Tensile Strength – Warp	ASTM D-4632	180	LB
Tensile Strength – Fill	ASTM D-4632	117	LB
Trapezoid Tear – Warp	ASTM D-4533	84	LB
Trapezoid Tear – Fill	ASTM D-4533	65	LB
Bursting Strength	ASTM D-3786	285	PSI
Puncture Strength	ASTM D-4833	75	LB
Water Permeability	ASTM D-4491	9.0	(GAL /MIN / SQFT)
UV Resistance	ASTM D-4355	More than 70% retention in original Tensile strength after 2500 hours	
Thickness		11 mils	

Date: 01/29/08. This data sheet supersedes all previously issued data.

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is to the best of our knowledge and belief, accurate and reliable as of the date compiled, however, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. We do not accept liability for any loss or damage that may occur from the use of this information nor do we offer any warranty against patent infringement.